Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-RW-2021-06-15-14 **Date: 08/04/2021**

: Improvements to Roads and Drains in Ward No.07 Byatarayanapura

: Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Reference : EE(Project)/Ynk Zone/WO/154/2020-21

: 03-04-21

: Cement Concrete Pavement, (1st A cross Road)

Type /Size : 150X150X150 mm

Age : M30 / 7 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 08/04/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement, (1st A cross Road)	M30	01/04/2021	08/04/2021	149.33 X 151.65 X 149.20	22646	**8.332**	583.1	25.7	25.7
Cement Concrete Pavement, (1st A cross Road)	M30	01/04/2021	08/04/2021	151.50 X 151.66 X 151.95	22977	**8.013**	616.6	26.8	
Cement Concrete Pavement, (1st A cross Road)	M30	01/04/2021	08/04/2021	149.43 X 149.71 X 150.25	22371	**8.402**	548.5	24.5	

Results obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-RW-2021-06-15-14 **Date: 29/04/2021**

: Improvements to Roads and Drains in Ward No.07 Byatarayanapura

: Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Reference : EE(Project)/Ynk Zone/WO/154/2020-21

: 03-04-21

: Cement Concrete Pavement, (1st A cross Road)

Size : 150X150X150 mm

Age : M30 / 28 Days Compressive Strength

codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 29/04/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement, (1st A cross Road)	M30	01/04/2021	29/04/2021	151.44 X 150.79 X 149.63	22837	**8.012**	771.6	33.8	33.3
Cement Concrete Pavement, (1st A cross Road)	M30	01/04/2021	29/04/2021	149.99 X 151.69 X 149.43	22753	**8.139**	736.0	32.3	
Cement Concrete Pavement, (1st A cross Road)	M30	01/04/2021	29/04/2021	150.74 X 151.08 X 151.41	22774	**8.243**	769.1	33.8	

obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-RW-2021-06-15-14** **Date: 14/04/2021**

: Improvements to Roads and Drains in Ward No.07 Byatarayanapura

: Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

: EE(Project)/Ynk Zone/WO/154/2020-21

: 09-04-21

: Cement Concrete Pavement, (11th Cross Yogesh nagara)

: 150X150X150 mm

: M30 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 14/04/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement, (11th Cross Yogesh nagara)	M30	07/04/2021	14/04/2021	150.58 X 151.46 X 150.85	22807	**8.332**	584.3	25.6	25.2
Cement Concrete Pavement, (11th Cross Yogesh nagara)	M30	07/04/2021	14/04/2021	149.80 X 149.49 X 151.90	22393	**8.013**	584.4	26.1	
Cement Concrete Pavement, (11th Cross Yogesh nagara)	M30	07/04/2021	14/04/2021	149.57 X 149.25 X 151.14	22323	**8.402**	536.5	24.0	

obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-RW-2021-06-15-14** **Date: 05/05/2021**

: Improvements to Roads and Drains in Ward No.07 Byatarayanapura

: Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Reference : EE(Project)/Ynk Zone/WO/154/2020-21

: 09-04-21

: Cement Concrete Pavement, (11th Cross Yogesh nagara)

Type/ Size : 150X150X150 mm

Grade/Age : M30 / 28 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 05/05/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement, (11th Cross Yogesh nagara)	M30	07/04/2021	05/05/2021	151.23 X 151.37 X 150.29	22892	**8.012**	762.6	33.3	33.2
Cement Concrete Pavement, (11th Cross Yogesh nagara)	M30	07/04/2021	05/05/2021	150.21 X 151.16 X 150.89	22707	**8.139**	743.2	32.7	
Cement Concrete Pavement, (11th Cross Yogesh nagara)	M30	07/04/2021	05/05/2021	151.94 X 150.23 X 150.33	22827	**8.243**	768.3	33.7	

obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-RW-2021-06-15-14 **Date: 14/04/2021**

: Improvements to Roads and Drains in Ward No.07 Byatarayanapura

: Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Reference : EE(Project)/Ynk Zone/WO/154/2020-21

: 09-04-21

: Cement Concrete Pavement, (9th Cross Road-Yogesh nagara)

Size : 150X150X150 mm

Age : M30 / 7 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 14/04/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement, (9th Cross Road-Yogesh nagara)	M30	07/04/2021	14/04/2021	151.15 X 149.20 X 149.36	22552	**8.332**	576.0	25.5	25.4
Cement Concrete Pavement, (9th Cross Road-Yogesh nagara)	M30	07/04/2021	14/04/2021	151.85 X 151.43 X 149.94	22995	**8.013**	606.2	26.4	
Cement Concrete Pavement, (9th Cross Road-Yogesh nagara)	M30	07/04/2021	14/04/2021	149.70 X 150.32 X 149.46	22503	**8.402**	546.9	24.3	

Results obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-RW-2021-06-15-14** **Date: 05/05/2021**

Name : Improvements to Roads and Drains in Ward No.07 Byatarayanapura

: Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Reference : EE(Project)/Ynk Zone/WO/154/2020-21

Receipt : 09-04-21

ID : Cement Concrete Pavement, (9th Cross Road-Yogesh nagara)

Type /Size : 150X150X150 mm

grade/Age : M30 / 28 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Test : 05/05/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement, (9th Cross Road-Yogesh nagara)	M30	07/04/2021	05/05/2021	149.43 X 151.86 X 150.02	22693	**8.012**	768.0	33.8	
Cement Concrete Pavement, (9th Cross Road-Yogesh nagara)	M30	07/04/2021	05/05/2021	150.41 X 149.52 X 149.59	22489	**8.139**	736.7	32.8	33.5
Cement Concrete Pavement, (9th Cross Road-Yogesh nagara)	M30	07/04/2021	05/05/2021	149.47 X 149.48 X 149.95	22342	**8.243**	755.3	33.8	

obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-RW-2021-06-15-14** **Date: 19/04/2021**

Name : Improvements to Roads and Drains in Ward No.07 Byatarayanapura

: Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

's Reference : EE(Project)/Ynk Zone/WO/154/2020-21

Receipt : 14-04-21

ID : Cement Concrete Pavement, (Green Elite Opposite Road)

Type /Size : 150X150X150 mm

grade/Age : M30 / 7 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Test : 19/04/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement, (Green Elite Opposite Road)	M30	12/04/2021	19/04/2021	151.82 X 151.38 X 151.71	22982	**8.332**	594.6	25.9	25.6
Cement Concrete Pavement, (Green Elite Opposite Road)	M30	12/04/2021	19/04/2021	151.20 X 149.42 X 149.10	22593	**8.013**	595.5	26.4	
Cement Concrete Pavement, (Green Elite Opposite Road)	M30	12/04/2021	19/04/2021	149.59 X 150.40 X 150.37	22498	**8.402**	552.8	24.6	

obtained are satisfactory as per standard requirements.

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-RW-2021-06-15-14 **Date: 10/05/2021**

: Improvements to Roads and Drains in Ward No.07 Byatarayanapura

: Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

: EE(Project)/Ynk Zone/WO/154/2020-21

: 14-04-21

: Cement Concrete Pavement, (Green Elite Opposite Road)

: 150X150X150 mm

: M30 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 10/05/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement, (Green Elite Opposite Road)	M30	12/04/2021	10/05/2021	151.95 X 150.10 X 151.77	22809	**8.012**	754.9	33.1	33.0
Cement Concrete Pavement, (Green Elite Opposite Road)	M30	12/04/2021	10/05/2021	150.99 X 150.76 X 150.50	22764	**8.139**	745.5	32.7	
Cement Concrete Pavement, (Green Elite Opposite Road)	M30	12/04/2021	10/05/2021	150.28 X 149.53 X 150.82	22471	**8.243**	746.3	33.2	

Results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-RW-2021-06-15-14** **Date: 19/04/2021**

: Improvements to Roads and Drains in Ward No.07 Byatarayanapura

: Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Reference : EE(Project)/Ynk Zone/WO/154/2020-21

: 14-04-21

: Cement Concrete Pavement, (Mariyappana Palya-1st Cross Road)

/Size : 150X150X150 mm

grade/Age : M30 / 7 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 19/04/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
ement Concrete Pavement, Mariyappana Palya-1st Cross Road)	M30	12/04/2021	19/04/2021	149.20 X 151.72 X 150.91	22637	**8.332**	580.2	25.6	25.5
ement Concrete Pavement, Mariyappana Palya-1st Cross Road)	M30	12/04/2021	19/04/2021	149.32 X 151.54 X 149.63	22628	**8.013**	596.0	26.3	
ement Concrete Pavement, Mariyappana Palya-1st Cross Road)	M30	12/04/2021	19/04/2021	151.72 X 149.08 X 151.85	22619	**8.402**	558.1	24.7	

obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-RW-2021-06-15-14** **Date: 10/05/2021**

: Improvements to Roads and Drains in Ward No.07 Byatarayanapura

: Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Reference : EE(Project)/Ynk Zone/WO/154/2020-21

: 14-04-21

: Cement Concrete Pavement, (Mariyappana Palya-1st Cross Road)

Type /Size : 150X150X150 mm

grade/Age : M30 / 28 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 10/05/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement, Mariyappana Palya-1st Cross Road)	M30	12/04/2021	10/05/2021	151.03 X 149.38 X 151.86	22560	**8.012**	758.6	33.6	33.1
Cement Concrete Pavement, Mariyappana Palya-1st Cross Road)	M30	12/04/2021	10/05/2021	149.09 X 149.43 X 149.27	22279	**8.139**	718.3	32.2	
Cement Concrete Pavement, Mariyappana Palya-1st Cross Road)	M30	12/04/2021	10/05/2021	151.38 X 149.86 X 150.35	22686	**8.243**	755.6	33.3	

obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-RW-2021-06-15-14** **Date: 24/04/2021**

Name : Improvements to Roads and Drains in Ward No.07 Byatarayanapura

: Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Reference : EE(Project)/Ynk Zone/WO/154/2020-21

Receipt : 19-04-21

ID : Cement Concrete Pavement, (Mariyappana Palya-2nd Cross Road)

Type /Size : 150X150X150 mm

grade/Age : M30 / 7 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 24/04/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement, (Mariyappana Palya-2nd Cross Road)	M30	17/04/2021	24/04/2021	149.40 X 149.33 X 149.96	22309	**8.332**	577.9	25.9	25.5
Cement Concrete Pavement, (Mariyappana Palya-2nd Cross Road)	M30	17/04/2021	24/04/2021	150.13 X 151.16 X 150.54	22694	**8.013**	596.8	26.3	
Cement Concrete Pavement, (Mariyappana Palya-2nd Cross Road)	M30	17/04/2021	24/04/2021	149.13 X 150.60 X 150.27	22459	**8.402**	545.6	24.3	

obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

CIVIL Pro Sig. Date BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-RW-2021-06-15-14** **Date: 15/05/2021**

: Improvements to Roads and Drains in Ward No.07 Byatarayanapura

: Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Reference : EE(Project)/Ynk Zone/WO/154/2020-21

Receipt : 19-04-21

ID : Cement Concrete Pavement, (Mariyappana Palya-2nd Cross Road)

Type /Size : 150X150X150 mm

grade/Age : M30 / 28 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Test : 15/05/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement, Mariyappana Palya-2nd Cross Road)	M30	17/04/2021	15/05/2021	150.98 X 151.00 X 150.68	22799	**8.012**	774.7	34.0	33.4
Cement Concrete Pavement, Mariyappana Palya-2nd Cross Road)	M30	17/04/2021	15/05/2021	149.61 X 151.12 X 149.36	22609	**8.139**	736.4	32.6	
Cement Concrete Pavement, Mariyappana Palya-2nd Cross Road)	M30	17/04/2021	15/05/2021	150.76 X 150.96 X 151.67	22759	**8.243**	766.6	33.7	

obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-RW-2021-06-15-14** **Date: 24/04/2021**

Name : Improvements to Roads and Drains in Ward No.07 Byatarayanapura

: Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

's Reference : EE(Project)/Ynk Zone/WO/154/2020-21

Receipt : 19-04-21

ID : Cement Concrete Pavement, (Nethajinagara)

Type /Size : 150X150X150 mm

grade/Age : M30 / 7 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Test : 24/04/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement, (Nethajinagara)	M30	17/04/2021	24/04/2021	150.78 X 150.60 X 150.76	22708	**8.332**	586.3	25.8	25.6
Cement Concrete Pavement, (Nethajinagara)	M30	17/04/2021	24/04/2021	149.76 X 149.44 X 149.68	22380	**8.013**	586.0	26.2	
Cement Concrete Pavement, (Nethajinagara)	M30	17/04/2021	24/04/2021	150.88 X 149.54 X 150.99	22562	**8.402**	556.4	24.7	

obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-RW-2021-06-15-14** **Date: 15/05/2021**

Project Name : Improvements to Roads and Drains in Ward No.07 Byatarayanapura

Agency : Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Customer's Reference : EE(Project)/Ynk Zone/WO/154/2020-21

Date of Receipt : 19-04-21

Customer ID : Cement Concrete Pavement, (Nethajinagara)

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/05/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement, (Nethajinagara)	M30	17/04/2021	15/05/2021	151.95 X 151.09 X 151.01	22958	**8.012**	777.1	33.8	33.3
2	Cement Concrete Pavement, (Nethajinagara)	M30	17/04/2021	15/05/2021	151.15 X 151.68 X 150.18	22926	**8.139**	752.4	32.8	
3	Cement Concrete Pavement, (Nethajinagara)	M30	17/04/2021	15/05/2021	150.19 X 151.62 X 151.01	22772	**8.243**	755.0	33.2	

Results obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

CIVIL Pro Sig..... Date

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-RW-2021-06-15-14** **Date: 28/04/2021**

Project Name : Improvements to Roads and Drains in Ward No.07 Byatarayanapura

Agency : Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Customer's Reference : EE(Project)/Ynk Zone/WO/154/2020-21

Date of Receipt : 23-04-21

Customer ID : Cement Concrete Pavement, (Jakkur Layout-11th B Cross)

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 28/04/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement, (Jakkur Layout-11th B Cross)	M30	21/04/2021	28/04/2021	150.11 X 150.28 X 149.26	22558	**8.332**	578.5	25.6	25.5
2	Cement Concrete Pavement, (Jakkur Layout-11th B Cross)	M30	21/04/2021	28/04/2021	151.85 X 150.17 X 149.16	22802	**8.013**	611.2	26.8	
3	Cement Concrete Pavement, (Jakkur Layout-11th B Cross)	M30	21/04/2021	28/04/2021	150.42 X 150.03 X 150.82	22567	**8.402**	545.4	24.2	

Remarks: The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro

R KARTHIK REDDY

Authorized Signatory

Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-RW-2021-06-15-14** **Date: 19/05/2021**

Project Name : Improvements to Roads and Drains in Ward No.07 Byatarayanapura

Agency : Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Customer's Reference : EE(Project)/Ynk Zone/WO/154/2020-21

Date of Receipt : 23-04-21

Customer ID : Cement Concrete Pavement, (Jakkur Layout-11th B Cross)

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/05/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement, (Jakkur Layout-11th B Cross)	M30	21/04/2021	19/05/2021	150.97 X 149.51 X 149.89	22571	**8.012**	754.0	33.4	33.1
2	Cement Concrete Pavement, (Jakkur Layout-11th B Cross)	M30	21/04/2021	19/05/2021	150.63 X 149.99 X 151.37	22593	**8.139**	725.0	32.1	
3	Cement Concrete Pavement, (Jakkur Layout-11th B Cross)	M30	21/04/2021	19/05/2021	149.04 X 151.75 X 149.36	22617	**8.243**	761.8	33.7	

The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-RW-2021-06-15-14** **Date: 28/04/2021**

Project Name : Improvements to Roads and Drains in Ward No.07 Byatarayanapura

Agency : Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Customer's Reference : EE(Project)/Ynk Zone/WO/154/2020-21

Date of Receipt : 23-04-21

Customer ID : Cement Concrete Pavement, (Vayunandana Layout-2nd Cross Road)

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 28/04/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement, (Vayunandana Layout-2nd Cross Road)	M30	21/04/2021	28/04/2021	150.69 X 149.24 X 151.32	22489	**8.332**	582.6	25.9	25.6
2	Cement Concrete Pavement, (Vayunandana Layout-2nd Cross Road)	M30	21/04/2021	28/04/2021	151.98 X 149.24 X 150.02	22682	**8.013**	595.4	26.3	
3	Cement Concrete Pavement, (Vayunandana Layout-2nd Cross Road)	M30	21/04/2021	28/04/2021	151.20 X 149.54 X 149.01	22610	**8.402**	556.7	24.6	

The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-RW-2021-06-15-14**

Date: 19/05/2021

Project Name : Improvements to Roads and Drains in Ward No.07 Byatarayanapura

Agency : Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Customer's Reference : EE(Project)/Ynk Zone/WO/154/2020-21

Date of Receipt : 23-04-21

Customer ID : Cement Concrete Pavement, (Vayunandana Layout-2nd Cross Road)

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/05/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement, (Vayunandana Layout-2nd Cross Road)	M30	21/04/2021	19/05/2021	151.34 X 149.79 X 149.02	22670	**8.012**	758.1	33.4	33.2
2	Cement Concrete Pavement, (Vayunandana Layout-2nd Cross Road)	M30	21/04/2021	19/05/2021	149.28 X 149.86 X 150.35	22372	**8.139**	720.8	32.2	
3	Cement Concrete Pavement, (Vayunandana Layout-2nd Cross Road)	M30	21/04/2021	19/05/2021	150.94 X 150.09 X 150.69	22655	**8.243**	768.9	33.9	

The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-RW-2021-06-15-14** **Date: 03/05/2021**

Project Name : Improvements to Roads and Drains in Ward No.07 Byatarayanapura

Agency : Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Customer's Reference : EE(Project)/Ynk Zone/WO/154/2020-21

Date of Receipt : 28-04-21

Customer ID : Cement Concrete Pavement, (Vayunandana Layout-4th Cross Road)

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 03/05/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement, (Vayunandana Layout-4th Cross Road)	M30	26/04/2021	03/05/2021	150.38 X 151.76 X 150.85	22822	**8.332**	592.3	26.0	25.5
2	Cement Concrete Pavement, (Vayunandana Layout-4th Cross Road)	M30	26/04/2021	03/05/2021	149.67 X 149.14 X 151.39	22321	**8.013**	584.5	26.2	
3	Cement Concrete Pavement, (Vayunandana Layout-4th Cross Road)	M30	26/04/2021	03/05/2021	149.12 X 150.28 X 151.24	22410	**8.402**	545.5	24.3	

The results obtained are satisfactory as per standard requirements.

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 24/05/2021

Lab ID : CP-RW-2021-06-15-14
Project Name : Improvements to Roads and Drains in Ward No.07 Byatarayanapura
Agency : Sri. M Prakash, #41, 2nd Cross, Venkatappa Layout, Amruthahalli, Bangalore-92.

Customer's Reference : EE(Project)/Ynk Zone/WO/154/2020-21
Date of Receipt : 28-04-21
Customer ID : Cement Concrete Pavement, (Vayunandana Layout-4th Cross Road)
Sample Type /Size : 150X150X150 mm
Sample grade/Age : M30 / 28 Days Compressive Strength
Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test : 24/05/2021

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement, (Vayunandana Layout-4th Cross Road)	M30	26/04/2021	24/05/2021	150.01 X 150.42 X 151.83	22564	**8.012**	746.8	33.1	33.1
2	Cement Concrete Pavement, (Vayunandana Layout-4th Cross Road)	M30	26/04/2021	24/05/2021	149.80 X 149.20 X 150.90	22351	**8.139**	722.8	32.3	
3	Cement Concrete Pavement, (Vayunandana Layout-4th Cross Road)	M30	26/04/2021	24/05/2021	149.61 X 151.52 X 149.14	22669	**8.243**	768.6	33.9	

The results obtained are satisfactory as per standard requirements.

FOR CIVIL Pro.

B KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES